



Formazione Construction	Ø Fune Ø Rope mm	Ø Filo Ø Wire mm	Peso fune per 100 m Weight of rope per 100 m kg	Carico di rottura minimo Min breaking force		
				daN	kgf	
<b>Acciaio zincato</b> - Classe 6x19 - PPC ISO 2408 - Resistenza fili 1960 N/mm <sup>2</sup>			<b>Galvanised steel</b> - Class 6x19 - PPC ISO 2408 - Wire strength 1960 N/mm <sup>2</sup>			
<b>S1PPC</b> 114 fili / wires 6x19 SEALE - PPC Crociata destra Right regular lay Cod. 75.550 	4	0.26	5.5	961	980	
	5	0.32	9.0	1510	1530	
	6	0.48	13.0	2600	2650	
	7	0.56	18.1	3350	3410	
	8	0.64	23.6	4320	4400	
	9	0.72	30.0	5530	5630	
	10	0.80	36.8	6830	6960	
	11	0.88	44.6	7350	7490	
	12	0.96	52.9	8730	8890	
<b>Acciaio zincato</b> - Classe 6x19 - IWRC ISO 2408 - Resistenza fili 1770 N/mm <sup>2</sup>			<b>Galvanised steel</b> - Class 6x19 - IWRC ISO 2408 - Wire strength 1770 N/mm <sup>2</sup>			
<b>S2</b> 114 fili / wires 6x19 SEALE - IWRC Crociata destra Right regular lay Cod. 75.624 	6	0.48	14.8	2450	2500	
	7	0.56	20.1	3220	3280	
	8	0.64	26.3	4200	4280	
	9	0.72	33.2	5310	5410	
	10	0.80	41.0	6560	6690	
	11	0.88	49.6	7950	8100	
	12	0.96	59.1	9440	9620	